



TIMBERSHADES

SOLID/OPAQUE EXTERIOR 100% ACRYLIC SIDING STAIN

185

PREMIUM SERIES
EXTERIOR
SOLID OPAQUE
185
TIMBERSHADES
100% ACRYLIC

TIMBERSHADES SOLID OPAQUE ACRYLIC STAIN is a premium 100% acrylic opaque wood stain that provides long lasting color and weather protection on exterior siding. Formulated using the same thixotropic technology as our other exterior products enables the pickup and release from the brush for faster and cleaner application.

TIMBERSHADES SOLID OPAQUE ACRYLIC Stain's high hiding acrylic formula provides a flexible coating with excellent UV protection perfect for Wisconsin seasonal changes. The 100% acrylic formula of TIMBERSHADES SOLID OPAQUE ACRYLIC STAIN makes it a fantastic maintenance stain that is flexible, resists fading and will never chalk. Best suited for use on vertical previously stained shake, siding, fencing, and most hardboard surfaces.

COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	62 g/L 0.52 lb./Gal

RECOMMENDED USAGE

- For Exterior Use
- Vertical Surfaces Only
- Previously Stained Shake, Siding, Fencing, and Most Hardboard Surfaces

PERFORMANCE & FEATURES

- Easy Brushability
- Advanced Color Protection
- Mildew Resistant
- Strong Adhesion

BENEFITS

Advanced Color Protection: The 100% acrylic formula produces outstanding adhesion, color retention and flexibility that will resist mildew, fade, peeling, and blistering.

Clean & Easy Application: Thixotropic technology creates a thick, hearty feel yet the stain still glides off the brush. The “drip-less” advantage helps to cut back on drips and runs in your finish with less fatigue.

Excellent Appearance: This full bodied stain provides a rich appearance that will not leave the wood looking dry and dull.

PRODUCT SPECIFICATIONS

Vehicle Type: 100% Acrylic

Color Tinting: White, Tint Bases, and Standard Colors

Gloss: Flat

2-6 units @ 60°

Solid Content: Weight: 53% ± 2

Volume: 36% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 2 Hours

To recoat: 4 Hours

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating.

Theoretical Coverage:

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.3 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



TIMBERSHADES

SOLID/OPAQUE EXTERIOR 100% ACRYLIC SIDING STAIN

185

PREMIUM SERIES
EXTERIOR
SOLID OPAQUE
185
TIMBERSHADES
100% ACRYLIC

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY PRIMING RECOMMENDATIONS

Wood Surfaces: Self Priming (requires 2 coats); PRIMEKOTE, 111 for Cedar and Redwood. All other species optional PRIMEGUARD, 112.

Aluminum Siding: Self Priming (requires 2 coats) or METALGUARD ACRYLIC DTM Primer/Finish, 338.

Galvanized Metal: Self Priming (requires 2 coats) or METALGUARD ACRYLIC DTM Primer/Finish, 338.

Steel: Metalguard Rust Inhibitive Primer, 330.

CMU, Concrete Block and Split Face: GRIPCRETE FILL KOTE HD BLOCK FILLER, 181.

Masonry/Stucco: Self Priming or GRIPCRETE MASONRY/PLASTER PRIMER, 166.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, or airless spray. If sprayed, product should be back-rolled or brushed to properly work into wood. Apply generously, working to a wet edge using overlapping strokes. Work entire length of 2-3 boards to avoid lap marks. Note: two coats of 185 are recommended to achieve the best performance, durability, and uniformity. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .50 GPM, 2800 PSI, .017-.019" Tip

HVLP: Not Recommended

Roller: 1/2" - 1" nap synthetic cover

Brush: 100% Nylon or Synthetic Blend