



FARM & RANCH

SATIN EXTERIOR ALKYD BARN PAINT - RED

200

PROFESSIONAL SERIES
EXTERIOR
SATIN
200
FARM & RANCH

FARM AND RANCH PREMIUM is our highest quality waterborne coating for agricultural structures. These products are formulated with a special alkyd-acrylic resin to provide lasting adhesion and color retention. Designed for self-priming application on weathered wood produces bright colors that resist chipping, peeling, and blistering keeping barns looking sharp for years to come. The high hiding finish is formulated at our Wisconsin-based factory to match the classic red and white barn colors.

Our FARM AND RANCH products have been trusted to protect and beautify Wisconsin's family farms for decades. With updated adhesion qualities, they can be applied to old and new barn boards and prepared metal siding. It can be used on many projects including barns, out buildings, bins, fences, and more.

COMPLIANCE & CERTIFICATION

Gloss Level	4
VOC Content	236 g/L 1.97 lb./Gal

PERFORMANCE & FEATURES

- High-Solids Formula
- Self-Priming Finish
- Pre-mixed Red
- Maximum Weather Protection

BENEFITS

High-Solids Formula: The high-solids formula creates a strong, durable barrier for longer protection from Wisconsin's weather extremes.

Pre-Mixed Red Formula: Factory tinted red formula provides exceptional coverage and color retention on weathered wood providing a bright, long-lasting finish.

Faster Job Completion: Self-priming technology with over double the volume solids of traditional barn paints allows for faster job completion saving time and labor on each project.

PRODUCT SPECIFICATIONS

Vehicle Type: Alkyd Oil

Color Tinting: Red. Do Not Tint.

Gloss: Satin

25-35 units @ 60°

Solid Content: Weight: 83% ± 2

Volume: 69% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 12-16 Hours

To recoat: Overnight

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating.

Theoretical Coverage:

Apply at 430 sq. ft./gal. to achieve

3.0 mils Wet Film Thickness

2.0 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Contains linseed oil. Rags or clothing soaked with this product should be immersed entirely in water until disposal to prevent spontaneous combustion
- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY PRIMING RECOMMENDATIONS

Wood Surfaces: Self Priming (requires 2 coats); PRIMEKOTE, 111 for Cedar and Redwood. All other species optional PRIMEGUARD, 112.

Aluminum Siding: Self Priming (requires 2 coats) or METALGUARD ACRYLIC DTM Primer/Finish, 338.

Galvanized Metal: Self Priming (requires 2 coats) or METALGUARD ACRYLIC DTM Primer/Finish, 338.

Steel: METALGUARD Rust Inhibitive Primer, 330.

CMU, Concrete Block and Split Face: GRIPCRETE HD Block Filler, 181.

Masonry/Stucco: Self Priming or GRIPCRETE Masonry/Plaster Primer, 166.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Surfaces should be dry prior to paint application. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with mineral spirits immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .70 GPM, 2500 PSI, .019-.021" Tip

HVLP: Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

Roller: 3/8" - 3/4" nap shed-resistant cover or lambswool cover

Brush: Natural China Bristle or Synthetic Blend