



PRODUCT DATA SHEET

Builder's Legacy

Premium Series
Interior Wall Primer/Sealer

WALL PREP PREMIUM EGGSHELL PRIMER/SEALER 226

DESCRIPTION

hallman/lindsay's **Builders Legacy** is our finest line of finishes designed for new drywall surfaces. All of our **Builders Legacy** products meet LEEDS criteria for new construction.

WALL PREP PREMIUM EGGSHELL PRIMER/SEALER is a top-line professional primer/sealer for unpainted drywall. It can be used under a wide range of finishes but it's higher sheen and superior sealing properties make it an excellent choice under Eggshell, Satin and Semi-Gloss finishes for new construction in the residential, multi-family, commercial and institutional markets.

FEATURES

- ✓ **Meets criteria set forth by the U.S. Green Building Council LEED-NC, version 2.2 and LEED-CI version 2.0.**
- ✓ Higher Sheen
- ✓ Excellent Sealing Properties
- ✓ High Hiding
- ✓ Excellent Coverage
- ✓ Quick-Dry
- ✓ Low-Odor
- ✓ Zero VOC per EPA Method 24
- ✓ **NOTE:** Material VOC content at or below 5g/L. This is based on an interpretation of the SCAQMD Rule 314 exemption for "Zero VOC equivalent" coatings.

PERFORMANCE DATA

Performance alternate for Federal Paint Specification TT-P-650 D

PRECAUTIONS/LIMITATIONS

- ✓ Please refer to Safety Data Sheets.
- ✓ Do not apply to "hot" plaster.
- ✓ Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

TECHNICAL DATA

- ✓ Color/Tinting:
Pro White. May be tinted with up to 4 ounces of low VOC universal colorants.
- ✓ Vehicle Type:
Vinyl copolymer
- ✓ Gloss
25 units @ 85°
- ✓ Percent Solid:
Weight: 42% ± 2
Volume: 28% ± 2
- ✓ Theoretical Coverage:
Apply at 400 sq.ft./gal. to achieve
4.0 mils Wet Film Thickness
1.1 mils Dry Film Thickness
When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.
- ✓ Drying Time at 77°F 50% R.H.:
To touch: 1 hour
Recoat: 2 hours
- ✓ Thinning/Cleanup:
Water
- ✓ VOC (EPA Method 24):
0 g/L 0 lbs./gal

Products of Hallman/Lindsay Paints
Sun Prairie, WI 53590

9 Finishes
Painting (09900)

TECHNICAL SERVICES



FACTORY & MAIN OFFICES
Ph. 608/834-8844
Fax 608/837-1064
www.hallmanlindsay.com

SURFACE PREPARATION

On drywall, all taped joints and nail heads should be sanded smooth and dusted. Patch all holes and cracks with an appropriate patching compound. Let dry thoroughly, sand smooth and prime. Surfaces must be dry, clean and free of dirt, oil or any other contaminants. Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

hallman/lindsay FINISH RECOMMENDATIONS

Excellent choice under Eggshell, Satin and Semi-Gloss finishes. May be used as a primer under appropriate **hallman/lindsay** top coats.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%.

EQUIPMENT REQUIREMENTS

- ✓ Airless: Minimum ½ GPM with .017" tip @ 2000 PSI
- ✓ Conventional: Binks #7 gun, 38 needle, 36 air nozzle, 38 fluid nozzle, 9.3 CFM @ 30 PSI
- ✓ HVLP: Twin-stage turbine, 5–8 PSI, .051 to .070 projector set
- ✓ Roller: ¼" – ½" nap shed-resistant cover or lambs wool cover
- ✓ Brush: 100% nylon or synthetic blend



FACTORY & MAIN OFFICES

1717 N. Bristol Street ☒ Sun Prairie, WI 53590
☎ (608) 834-8844 ☎ FAX (608) 837-1064 🌐 www.hallmanlindsay.com

This technical bulletin is intended only as a source of information and, to the best of our knowledge, the information herein is correct. However, since conditions of the use of our product are beyond our control, the final determination of any information or of the material for the use contemplated is the sole responsibility of the user.