

# DROP DRY

## EGGSHELL INTERIOR ALKYD DRYFALL

### 242

DROP DRY ALKYD is an interior alkyd dryfall designed for professional spray application. Overspray falls dry at or above 10 feet at 77°F with 50% relative humidity for easy sweep clean-up. Solvent-based formulation provides exceptional adhesion and helps prevent flash-rust on metal surfaces. Higher levels of titanium dioxide in the formulation means increased coverage and hide allowing for faster application.

DROP DRY ALKYD products are designed to improve light reflectance and aesthetics in interior cavernous spaces. Formulated for improved adhesion, this product allows for application to surfaces ranging from structural steel to paneling. It is ideally used in commercial and industrial buildings, including warehouses, arenas, and manufacturing facilities.

#### COMPLIANCE & CERTIFICATION

Gloss Level	3
VOC Content	395 g/L 3.30 lb./Gal

#### RECOMMENDED USAGE

- For Interior Use
- Ideal for Vertical Overhead Surfaces
- Excellent For Ceilings, Trusses, Pipers, and Ductwork
- Spray Application Only

#### PERFORMANCE & FEATURES

- High-Hiding White
- Excellent Adhesion
- Flash-Rust Resistant
- Dry Drop (10+ ft. under normal conditions)

#### BENEFITS

**Solvent-Based Formula:** Alkyd dryfall provides improved flash rust resistance and improved adhesion to marginally prepared surfaces versus traditional waterborne products.

**High-Hiding Formula:** Formulated with higher levels of titanium dioxide provides improved protection while increasing hide and coverage rates.

**Custom Colors Available:** Available in standard deck white, white, black and a tintable neutral base. Qualifying orders are available in factory batched colors in as short as two business days. Ask a Hallman Lindsay sales representative for more information

#### PRODUCT SPECIFICATIONS

**Vehicle Type:** Alkyd

**Color Tinting:** Deck White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.

**Gloss:** Eggshell

15-25 units @ 60°

**Solid Content:** Weight: 54% ± 2

Volume: 35% ± 2

**Drying Time:** (75° F. & 50% R.H.)

To touch: 15 Minutes

To recoat: 4 Hours

*Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating*

#### **Theoretical Coverage:**

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.9 mils Dry Film Thickness

*When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.*

#### PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Do not apply to non-primed aluminum or galvanized metal.
- Not for use on foil or vinyl backed insulation.
- For interior application only.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.

# DROP DRY

## EGGSHELL INTERIOR ALKYD DRYFALL

### 242

PROFESSIONAL SERIES  
INTERIOR  
EGGSHELL  
242  
DROP DRY

#### **SURFACE PREPARATION**

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

**Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**

#### **HALLMAN LINDSAY PRIMING RECOMMENDATIONS**

##### **New Work**

**Drywall:** Self-priming with two coats or Pro Wall Primer, 227.

**Plaster/Masonry:** GRIPCRETE Masonry/Plaster Primer, 166.

**Wood:** Self-priming with two coats or Enamel Undercoat, 231.

**Galvanized Surfaces:** Self-priming with two coats or METALGUARD ACRYLIC DTM Primer/Finish, 338.

**Steel Surfaces:** METALGUARD Rust Inhibitive Primer, 330.

**Block:** GRIPCRETE Block Filler, 184.

**Repaint:** Self-Priming

#### **APPLICATION**

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with mineral spirits immediately after use.

#### **EQUIPMENT REQUIREMENTS**

**Airless:** Minimum .70 GPM, 2700 PSI, .017-.019" Tip

**HVLP:** Not Recommended

**Roller:** Not Recommended

**Brush:** Not Recommended