



# BUILDER'S LEGACY

## MASTER KOTE FLAT

267

CLASSIC SERIES  
INTERIOR  
FLAT  
267  
MASTER KOTE

MASTER KOTE interior wall finishes are designed to meet the needs of today's professional applicator. As a part of the Builder's Legacy system, these products are formulated for easy, reliable application with good hide and touch-up qualities. The flat finish provides an ultra-flat sheen that reduces drywall imperfections in critical lighting. While the moisture-resistant eggshell finish provides an even, uniform sheen ideal for kitchens, bathrooms and traffic areas.

MASTER KOTE provides a high-hiding, uniform finish that meets the needs of today's production new construction market. The zero-VOC, LEED v4 Credit Eligible formulation works for commercial projects looking to meet the strictest air quality standards. These products are best used for painting drywall and cured plaster in residential, multi-family, institutional, and commercial buildings.

### COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	4.108 g/L 0.03 lb./Gal
LEED v4 Credit Eligible	YES

### RECOMMENDED USAGE

- For Interior Use
- Use in Residential, Multi-Family Commercial, and Institutional Construction

### PERFORMANCE & FEATURES

- High-Hiding Finish
- Excellent Walk-Away Appearance
- Easy Application and Touch-up
- Zero-VOC, LEED v4 Credit Eligible

### BENEFITS

**Construction-Focused Design:** Designed for high-hide and consistent touchup allows construction and maintenance projects to stay on schedule and on budget by avoiding call backs.

**Low-Odor, Zero-VOC Formulation:** This zero-VOC, LEED v4 Credit Eligible finish provides the performance needed for contractors, specifiers, property managers, and general contractors looking to strictest air quality standards.

**Local Manufacturing:** Local production and shipping allow for faster inventory turns and factory batched colors in as little as two business days. Consult your Hallman Lindsay representative for details.

### PRODUCT SPECIFICATIONS

**Vehicle Type:** Ethylene-Vinyl Acetate

**Color Tinting:** Pro White. May be tinted, up to 2 oz. per gallon, with low VOC colorants.

**Gloss:** Flat

0-3 units @ 60°

**Solid Content:** Weight: 50% ± 2

Volume: 30% ± 2

**Drying Time:** (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: 4 Hours

*Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating*

### Theoretical Coverage:

Apply at 300 sq. ft./gal. to achieve

6.0 mils Wet Film Thickness

1.9 mils Dry Film Thickness

*When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.*

### PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



# BUILDER'S LEGACY

## MASTER KOTE FLAT

### 267

CLASSIC SERIES  
INTERIOR  
FLAT  
267  
MASTER KOTE

#### **SURFACE PREPARATION**

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

**Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**

#### **HALLMAN LINDSAY PRIMING RECOMMENDATIONS**

**Drywall:** Premium Wall Primer, 220.

**Plaster/Masonry:** GRIPCRETE Masonry/Plaster Primer, 166.

**Wood:** Enamel Undercoat, 231.

**Galvanized Surfaces:** Enamel Undercoat, 231, METALGUARD ACRYLIC DTM Primer/Finish, 338.

**Steel Surfaces:** METALGUARD Rust Inhibitive Primer, 330

**Block:** GRIPCRETE HD Block Filler, 181.

**Repaint:** Self-Priming (requires two coats).

#### **APPLICATION**

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

#### **EQUIPMENT REQUIREMENTS**

**Airless:** Minimum .70 GPM, 2500 PSI, .017-.019" Tip

**HVLP:** Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

**Roller:** ½" - 1" nap shed-resistant or lambswool cover

**Brush:** 100% Nylon or Synthetic Blend