



BUILDER'S LEGACY

PROFESSIONAL PRIMER SURFACER

367

CLASSIC SERIES
INTERIOR
PRIME COAT
367
PRO PRIMER SURFACER

PROFESSIONAL PRIMER SURFACER is high-building primer/sealer formulated to improve finish coat performance on residential and commercial projects. The added film thickness helps to reduce signs of drywall repair and trade damage typically found in commercial construction. Improved film integrity creates a uniform porosity between drywall paper and point compound that is compatible with all interior finishes.

PROFESSIONAL PRIMER SURFACER is designed to minimize the minor surface imperfections found on walls and ceilings including nicks, dents, paper fuzz, and mud pinholes. Formulated specifically for professional spray application, it is ideally suited for commercial and production application.

COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	< 5 g/L < 0.042 lb./Gal
LEED v4 Credit Eligible	YES

RECOMMENDED USAGE

- For Interior New Drywall
- Use in Residential, Commercial, and Institutional Construction

PERFORMANCE & FEATURES

- High-Building Primer/Sealer
- Available in High and Low Viscosity
- Great Enamel Hold-Out
- LEED v4 Credit Eligible

BENEFITS

Custom-Tailored Application: Unique offering of multiple viscosity options for customized application tailed to professional sprayers.

Improved Drywall Finishing: Improve overall drywall appearance by smoothing out minor drywall imperfections while preparing surfaces for finish coats of any sheen level.

Environmentally Responsible Coating: This zero-VOC, LEED v4 credit eligible finish meets the performance needs of contractors, specifiers, and general contractors looking to meet the strictest air quality standards.

PRODUCT SPECIFICATIONS

Vehicle Type: Ethylene-Vinyl Acetate

Color Tinting: White. May be tinted, up to 2 oz. per gallon, with low/zero VOC colorants.

Gloss: Flat

0-4 units @ 60°

Solid Content: Weight: 58% ± 2

Volume: 37% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: Overnight

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 160 sq. ft./gal. to achieve

10.0 mils Wet Film Thickness

3.7 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- Must be topcoated.
- Joint compound must be completely dry.
- Not intended for use with epoxy topcoats.
- When top coating with higher sheens, apply 2 coats for full sheen development.



BUILDER'S LEGACY

PROFESSIONAL PRIMER SURFACER

367

CLASSIC SERIES
INTERIOR
PRIME COAT
367
PRO PRIMER SURFACER

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY FINISHING RECOMMENDATIONS

High-Performance Acrylic: Duratech and Aquapoxy 1 Series

Designer Finish: Pure and Lustre Series

Premium Finish: Wonderkote and Earthscapes Series

Professional Finish: Pro Kote and Renewal Series

Builder's Legacy Finishes: Master Kote, Velvet Armor, and Premium Smooth Hi-Build.

APPLICATION

Apply by airless spray for best results. May be applied by brush or roller; however, all properties related to hide and appearance may be affected. Surfaces should be dry prior to paint application. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum 1.20 GPM, 3000 PSI, .021-.027" Tip

HVLP: Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

Roller: 1/2" - 1" nap synthetic cover

Brush: 100% Nylon or Synthetic Blend