

STAINGUARD

INTERIOR/EXTERIOR 100% ACRYLIC STAIN BLOCKING PRIMER

526

PREMIUM SERIES
INTERIOR/EXTERIOR
SEMI-GLOSS
526
STAINGUARD

STAINGUARD is a premium acrylic stain blocking primer designed to block and seal typical household and commercial stains. This multi-purpose primer seals in stains such as marker, crayon, lipstick, graffiti, light water stains, and dark paint colors. The versatile 100% acrylic resin has excellent adhesion and flexibility allowing it to be used on a variety of interior and exterior surfaces. Its high hiding, waterborne formula provides a low-VOC, low odor, quick dry alternative to solvent-based primers.

Apply STAINGUARD to seal in stains on a variety of interior and exterior surfaces including wood, plaster, drywall, hardboard, masonry, ceilings, trim, acoustical ceiling ties, and other porous surfaces. Can be applied to new and previously painted surfaces. Severe stains may require multiple coats or an alternative system. May be used under conventional latex or alkyd topcoats.

COMPLIANCE & CERTIFICATION

Gloss Level	4
VOC Content	80.377 g/L 0.67 lb./Gal

PERFORMANCE & FEATURES

- Tough 100% Acrylic Formula
- Excellent Adhesion
- Interior and Exterior use
- Low Odor and Low-VOC

BENEFITS

100% Acrylic Resin: Premium resin provides exceptional adhesion for both interior and exterior projects.

Tough Stain Blocker: Tougher than ordinary universal primers, STAINGUARD simply blocks stains better. Blocks marker, crayon, lipstick, graffiti, water stains and much, much more.

Fast Drying: With a dry time of under an hour, you can prime and paint in the same day helping jobs get done more efficiently.

PRODUCT SPECIFICATIONS

Vehicle Type: Acrylic

Color Tinting: White. May be tinted, up to 4 oz. per gallon, with most universal colorants

Gloss: Semi-Gloss

30-40 units @ 60°

Solid Content: Weight: 43% ± 2

Volume: 33% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 30-40 Minutes

To recoat: 1 Hour

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.4 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



STAINGUARD

INTERIOR/EXTERIOR 100% ACRYLIC STAIN BLOCKING PRIMER
526

PREMIUM SERIES
INTERIOR/EXTERIOR
SEMI-GLOSS
526
STAINGUARD

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY FINISHING RECOMMENDATIONS

Interior

Latex Finishes: Compatible with all Hallman Lindsay waterborne interior finishes.

Alkyd Finishes: Duraguard Series.

Exterior

Latex Finishes: Compatible with all Hallman Lindsay waterborne exterior finishes.

Alkyd Finishes: Duraguard Series.

APPLICATION

Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Surfaces should be dry prior to paint application. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .50 GPM, 2750 PSI, .017-.019" Tip

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

Roller: ¼" - ½" nap shed-resistant cover or lambswool cover

Brush: 100% Nylon or Synthetic Blend