

JET DRY

GLOSS INTERIOR/EXTERIOR ALKYD-ACRYLIC ENAMEL

575

PROFESSIONAL SERIES
INTERIOR/EXTERIOR
GLOSS
575
JET DRY

JET DRY ACRYLIC ENAMEL is a premium solvent based acrylic enamel formulated for fast drying and rapid recoats. This high performance alkyd-acrylic provides a weather resistant finish that has good gloss and color retention. With a 15 minute dry time, you are able to spray out multiple coats and return to service the same day.

JET DRY ACRYLIC ENAMEL is formulated for professional spray application only. It is ideal for use on equipment, piping, machinery, structural steel, storage tanks, railings, furniture, and many other substrates. Can be applied over existing coatings only after test samples have confirmed compatibility of coatings.

COMPLIANCE & CERTIFICATION

Gloss Level	5
VOC Content	513 g/L 4.28 lb./Gal

RECOMMENDED USAGE

- For Interior and Exterior Use
- Prepared Wood, Galvanized, and Masonry Surfaces
- Use on Commercial, Manufacturing, and Light Industrial Construction

PERFORMANCE & FEATURES

- High Production Finish
- Fade Resistant Formula
- Fast Return to Service
- Weather Resistant Coating

BENEFITS

Fast Drying Formula: JET DRY's fast drying formula allows multiple coats to be sprayed in rapid succession for same-day coverage of dark and vibrant colors.

Quick Return to Service: Drying to the touch in 15 minutes allows doors and frames to be coated and closed quickly to secure buildings and minimize downtime.

Solvent-Based Acrylic: Solvent-based acrylic resins help reduce premature color fading and improve gloss retention.

PRODUCT SPECIFICATIONS

Vehicle Type: Acrylic Alkyd Co-Polymer

Color Tinting: White and Select Colors

Gloss: Gloss

80 Units @ 60°

Solid Content: Weight: 54% ± 2

Volume: 38% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 15 Minutes

To recoat: 8 Hours

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 350 sq. ft./gal. to achieve

4.5 mils Wet Film Thickness

1.7 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.
- Not intended for immersion service.
- For commercial/industrial use only.

JET DRY

GLOSS INTERIOR/EXTERIOR ALKYD-ACRYLIC ENAMEL

575

PROFESSIONAL SERIES
INTERIOR/EXTERIOR
GLOSS
575
JET DRY

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY PRIMING RECOMMENDATIONS

Interior

Wood Surfaces: Enamel Undercoat, 231.

Metal, Non-Ferrous: METALGUARD DTM Acrylic Primer/Finish, 338.

Metal, Ferrous: METALGUARD Rust Inhibitive Primer, 330.

Exterior

Wood Surfaces: PRIME GUARD, 112.

Metal, Non-Ferrous: METALGUARD DTM Acrylic Primer/Finish, 338.

Metal, Ferrous: METALGUARD Rust Inhibitive Primer, 330.

Repaint Surfaces: May be applied over existing coatings only after sample applications have been made to check the sensitivity of the existing coating. Surfaces must be primed and properly prepared if sensitivity or lifting occurs.

APPLICATION

Mix thoroughly before use. Apply by airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. Apply only if air, surface and material temperatures remain 50° F or above during application and drying. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with mineral spirits immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .70 GPM, 2500 PSI, .019-.021" Tip

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

Roller: Not Recommended

Brush: Not Recommended