



SUPREME FLAT

FLAT INTERIOR WALL PAINT

720

PROFESSIONAL SERIES
INTERIOR
FLAT
720
SUPREME FLAT

SUPREME FLAT is a professional grade wall finish designed to meet the needs for interior ongoing property maintenance. This unique product was created for easy transition from discontinued products from former regional manufacturers. The fast drying, high-viscosity formula provides good coverage allowing painted and affected areas to be quickly returned to service. With virtually no odor, this zero-VOC maintenance finish meets the most stringent air quality standards reducing downtimes and impact in occupied spaces.

SUPREME FLAT has been designed specifically for buildings and spaces requiring frequent maintenance painting and touch-up. It is ideally suited for multi-units, rental homes, and commercial retail spaces. May be used on a variety of interior surfaces such as drywall, plaster, masonry, wood, and properly primed metals.

COMPLIANCE & CERTIFICATION

Gloss Level	1
VOC Content	3.885 g/L 0.03 lb./Gal

RECOMMENDED USAGE

- For Interior Use
- Drywall and Plaster
- Masonry, Wood, And Primed Metals
- Multi-Unit, Rentals Homes, and Commercial Retail Spaces

PERFORMANCE & FEATURES

- Good Hide and Touch-up
- Low-Spatter Formula
- Low Odor, Zero-VOC, LEED v4 Compliant
- Easy Application

BENEFITS

Easy Product Crossover: Designed for easy transition from discontinued regional products. Ask your Hallman Lindsay sales representative for details.

Excellent Hide: High-hiding formula allows for great coverage over typical wear in traffic areas and occupied spaces.

Easy Touch-up and Application: The low-spatter, easy application formula allows for a forgiving finish that can be applied by painters of all skill levels.

PRODUCT SPECIFICATIONS

Vehicle Type: Ethylene-Vinyl Acetate

Color Tinting: White and Standard Colors

Gloss: Flat

0-4 units @ 60°

Solid Content: Weight: 50% ± 2

Volume: 32% ± 2

Drying Time: (75° F. & 50% R.H.)

To touch: 1 Hour

To recoat: 2 Hours

Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating

Theoretical Coverage:

Apply at 400 sq. ft./gal. to achieve

4.0 mils Wet Film Thickness

1.2 mils Dry Film Thickness

When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.

PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



SUPREME FLAT

FLAT INTERIOR WALL PAINT

720

PROFESSIONAL SERIES
INTERIOR
FLAT
720
SUPREME FLAT

SURFACE PREPARATION

Surfaces must be dry, clean and free of dust, dirt, grease, oil or any other contaminants that may prevent proper adhesion. All loose paint must be removed and glossy surfaces dulled by sanding. Plaster surfaces must be well cured, and porous masonry surfaces should be filled with block filler. Tape joints and nailheads on drywall should be sanded and dusted clean before finishing. Mud on joints and nailheads must be thoroughly cured before finishing to help avoid photographing. Galvanized surfaces shall have all oils removed prior to application of coating.

Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to www.epa.gov/lead.

HALLMAN LINDSAY PRIMING RECOMMENDATIONS

New Work

Drywall: Pro Wall Primer, 227.

Plaster/Masonry: GRIPCRETE Masonry/Plaster Primer, 166.

Wood: Enamel Undercoat, 231.

Galvanized Surfaces: Enamel Undercoat, 231 or METALGUARD DTM Acrylic Primer/Finish, 338.

Steel Surfaces: METALGUARD Rust Inhibitive Primer, 330.

Block: GRIPCRETE Block Kote Block Filler, 184.

Repaint: Self-Priming (requires two coats).

APPLICATION

Mix thoroughly before use. Apply by brush, roller, airless, HVLP or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Do not brush or roll excessively. Reducing material for spray application should not exceed 10%. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.

EQUIPMENT REQUIREMENTS

Airless: Minimum .70 GPM, 2500 PSI, .017-.019" Tip

HVLP: Twin-stage turbine, 5 – 8 PSI, .051 to .070 projector set

Roller: 1/2"-3/4" nap synthetic cover

Brush: 100% Nylon or Synthetic Blend