



# CLEARGUARD

## SEMI-GLOSS INTERIOR ALKYD SANDING SEALER

### V372

DESIGNER SERIES  
INTERIOR  
SEMI-GLOSS  
V372  
CLEARGUARD SANDING  
SEALER

CLEARGUARD SANDING SEALER / FINISH is designed to be a quick-dry high-building sanding sealer for interior wood surfaces. This fast-drying sealer provides exceptional build over bare wood and sands easily to a powder for smoother finishes. The unique formula allows multiple coats to be applied to reach a semigloss finish safe for use on vertical surfaces including trim, doors, and cabinetry.

CLEARGUARD is Hallman Lindsay's premium line of clear wood finishes designed to protect and enhance the natural beauty of wood. Whether used as part of the WOOD SHADES system or strictly as a sealer, these products can be used on new wood or when refinishing properly prepared interior wood surfaces.

#### COMPLIANCE & CERTIFICATION

Gloss Level	4
VOC Content	548 g/L 4.54 lb./Gal

#### RECOMMENDED USAGE

- For Interior Use
- Vertical Surfaces Only
- Cabinets, Doors, and Trim

#### PERFORMANCE & FEATURES

- Quick-Dry Formula
- Sealer & Finish Coat
- Easily Sands to a Powder
- Compatible With All Stains

#### BENEFITS

**Time & Material Savings:** This quick-dry sealer produces an easy-sand finish that requires less sanding for smoother woodwork. Faster film-build seals porous wood grain reducing the amount of topcoat needed to produce an even, uniform sheen.

**Sealer/Finish Technology:** Clearguard's Sealer/Finish technology allows multiple coats to be applied to produce a semi-gloss finish suited for doors, trim, and cabinets.

**Versatile Sealer:** Can be applied over a waterborne and alkyd stains. Dries to a hard finish allows for use on floors, furniture, cabinetry, and trim.

#### PRODUCT SPECIFICATIONS

**Vehicle Type:** Oil Modified Urethane

**Color Tinting:** Clear. Do Not Tint

**Gloss:** Semi-Gloss

30-50 units @ 60°

**Solid Content:** Weight: 33% ± 2

Volume: 25% ± 2

**Drying Time:** (75° F. & 50% R.H.)

To touch: 30 Minutes

To recoat: 2 Hours

*Extended drying time may be expected when conditions such as high humidity, high dew point, low temperature, etc. are present. Allow product to dry thoroughly before top coating.*

#### **Theoretical Coverage:**

Apply at 265-410 sq. ft./gal. to achieve

4.0-6.0 mils Wet Film

Thickness

1.1-1.7 mils Dry Film

Thickness

*When calculating working coverage, allow for application losses, texture and porosity of surface, application technique, etc.*

#### PRECAUTIONS/LIMITATIONS

- Please refer to Safety Data Sheets.
- Apply only if air, surface and material temperatures remain 50° F or above during application and drying.



# CLEARGUARD

## SEMI-GLOSS INTERIOR ALKYD SANDING SEALER

### V372

DESIGNER SERIES  
INTERIOR  
SEMI-GLOSS  
V372  
CLEARGUARD SANDING  
SEALER

### **SURFACE PREPARATION**

Surfaces must be dry, clean and free of dust, dirt, grease, wax, oil, chalk, rust or any other contaminants that may prevent proper adhesion. New wood should be stained and sealed before finishing. Previously stained, painted or varnished surfaces should be thoroughly sanded and dusted clean before applying finish. Two coats are recommended. Sand lightly and dust between coats.

**Warning! If you scrape, sand or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage, especially in children. Pregnant women should also avoid exposure. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the national lead information hotline at 1-800-424-LEAD (5323) or log on to [www.epa.gov/lead](http://www.epa.gov/lead).**

### **HALLMAN LINDSAY FINISHING RECOMMENDATIONS**

#### **New Work**

**Stain:** Woodshades Interior Stain Series.

**Sealer (optional):** Clearguard Alkyd Sanding Sealer, v372.

#### **Refinishing Work**

**Sealer (optional):** Clearguard Alkyd Sanding Sealer, v372.

**Top Coat:** Woodshades Clearguard Series.

**Repaint Surfaces:** May be applied over existing coatings only after sample applications have been made to check the sensitivity of the existing coating. Surfaces must be primed and properly prepared if sensitivity or lifting occurs.

### **APPLICATION**

Stir thoroughly before use. Shaking will cause Air bubbles to form in finish. Apply by brush, roller, airless, HVLP, or conventional spray. Flow and leveling is best achieved by applying a full, uniform coating and working to a wet edge using overlapping strokes. Surfaces should be dry prior to paint application. Sand lightly between coats with sandpaper or nylon abrasive, not steel wool, and remove any sanding dust. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with mineral spirits immediately after use.

### **EQUIPMENT REQUIREMENTS**

**Airless:** Minimum .50 GPM, 2500 PSI, .013-.015" Tip

**HVLP:** Twin-stage turbine, 5-8 PSI, .051 to .070 projector set

**Roller:** 1/4" nap shed-resistant or lambswool cover

**Brush:** 100% Nylon or Synthetic Blend