



PREMIUM
EXTERIOR

TIMBERSHADES
100% ACRYLIC SOLID

Hallman Lindsay serves the communities where we live and work. We provide expertise and quality products made and mixed in Wisconsin for over 60 years.

GREAT PAINT. GREAT PEOPLE.



100% ACRYLIC SOLID STAIN

TIMBERSHADES ACRYLIC SIDING STAIN is a 100% acrylic opaque wood stain that provides long lasting color and weather protection on exterior siding. Formulated using the same thixotropic technology as our other exterior products enables the pickup and release from the brush for faster and cleaner application. The high hiding acrylic formula provides a flexible coating with excellent UV protection perfect for Wisconsin seasonal changes.

TIMBERSHADES ACRYLIC SIDING STAIN is formulated specifically for exterior wood surfaces requiring an opaque finish. The acrylic formula makes it a fantastic maintenance stain that resists fading and will never chalk. It is best used for shakes, siding, fencing, and most hardboard surfaces. It is not recommended for decks, floors, or any horizontal surfaces.

FEATURES

- Easy Brushability
- Advanced Color Protection
- Mildew Resistant
- Strong Adhesion

BENEFITS

Advanced Color Protection

The 100% acrylic formula produces outstanding adhesion, color retention and flexibility that will resist mildew, fade, peeling, and blistering.

Clean & Easy Application

Thixotropic technology creates a thick, hearty feel yet the stain still glides off the brush. The "drip-less" advantage helps to cut back on drips and runs in your finish with less fatigue.

Excellent Appearance

This full bodied stain provides a rich appearance that will not leave the wood looking dry and dull.



TECHNICAL INFORMATION

BASES: FLAT - 185 SERIES

APPLICATION INFORMATION

Drying Time at 77° F 50% R.H:
 To Touch: 2 hours*
 Recoat: Overnight*
 * Cooler temperatures and higher relative humidity will extend dry times

Recommended Spreading Rate:

400 sq. ft./gal to achieve
 4.0 mils Wet Film Thickness
 1.3 mils Dry Film Thickness

Solids Content:

Volume: 35% ± 2 Weight: 49% ± 2

EQUIPMENT RECOMMENDATIONS

Roller: ½" - ¾" nap synthetic cover
Brush: 100% nylon or synthetic blend
Airless: Minimum ¼ GPM with .017" tip @ 2000 PSI
HVLP: Not recommended

SAFETY AND COMPLIANCE

VOC (EPA Method 24):
 0 g/L 0.0 lbs./Gal
MPI Category:
 16

PRIMING RECOMMENDATIONS

Wood Surfaces: Self Priming (requires 2 coats); Prime Kote, 111 for Cedar and Redwood. All other species optional Prime Guard, 112.
Aluminum Siding: Self Priming (requires 2 coats) or Metalguard DTM Acrylic Primer/Finish, 338.
Galvanized Metal: Self Priming (requires 2 coats) or Metalguard DTM Acrylic Primer/Finish, 338.
Steel: Metalguard Rust Inhibitive Primer, 330.
CMU, Concrete Block and Split Face: Grip-Crete Fill Kote HD Block Filler, 181.
Masonry/Stucco: Self Priming or Grip-Crete Masonry/Plaster Primer, 166.